

Technical Data Sheet
ULTRASHEEN® UV-8705BF

UV curable, benzophenone-free smooth dull coating

ACTEGA North America, Inc.
 1450 Taylors Lane, Cinnaminson, NJ 08077 US
 +1 800-255-0021
 info.ACTEGA.northamerica@altana.com
 www.actega.com

Product Description

UV curable, benzophenone-free smooth dull coating with a smooth finish and high scuff resistance

General Information	
Product Type	Coatings
Product Technology	UV curing
Field Of Application	Paperbased Packaging, Publication & Commercial, Advertising, Books, Corrugated, Cosmetic packaging, Direct Mail, Displays, Folded Boxes-Household/Hardware & Electronics/other non food, Folded Boxes-Personal Care/Cosmetics, Photo books, Shelf-ready packaging, Transport packaging
Properties	Benzophenone-Free, Chemical resistance, Good flow out, Good rub and scratch resistance, Good wetting on different printing inks, e. g. conventional, UV printing inks, web offset printing inks, make tests!, Proves in practice to be suitable as two-sided coating., Sutherland Rub Resistance, The coating contains optical brightener.

Application Method


- Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm

Substrate Recommendation

- Coated Board
- Coated Paper

Properties

- Gloss
- Flexibility
- Scuff Resistance
- Slip Surface Smoothness
- Reactivity
- Two Sided Coating



Technical Data Sheet
ULTRASHEEN® UV-8705BF

UV curable, benzophenone-free smooth dull coating

ACTEGA North America, Inc.
 1450 Taylors Lane, Cinnaminson, NJ 08077 US
 +1 800-255-0021
 info.ACTEGA.northamerica@altana.com
 www.actega.com

Product Characteristics			
Viscosity	• ~330 mPas +/- 30 (Centipoise at 25°C)		
Curing	• 125 - 150 fpm @ 300WPI		
Hot Foil Stamping	<input type="checkbox"/>	Glueability	<input type="checkbox"/>
Anti Penetration	<input type="checkbox"/>		

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

- Please clean machines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 20 - 30 Double Rubs
 * Estimated chemical resistance on press

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products’ properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.