

Technical Data Sheet ULTRASHEEN® UV-9671BF

UV curable gloss benzophenone-free foil stampable coating

ACTEGA North America, Inc. 1450 Taylors Lane, Cinnaminson, NJ 08077 US +1 800-255-0021

info.ACTEGA.northamerica@altana.com www.actega.com

Product Description

UV curable gloss benzophenone-free foil stampable coating

General Information			
Product Type	Coatings		
Product Technology	UV curing		
Field Of Application	Paperbased Packaging, Publication & Commercial, Advertising, Books, Commercial, Decorative packaging, exterior, Folded Boxes-Household/Hardware & Electronics/other non food, Other non-food, Shelf-ready packaging		
Properties	Benzophenone-Free, Good wetting on different printing inks, e. g. conventional, UV printing inks, web offset printing inks, make tests!, Print varnish to get glossy-, matte and/or trickle down effects by the inline coating with UV varnishes. The print varnish must be UV cured before overprinting., Proves in practice to be suitable as coating for the later counter glueing., The coating contains optical brightener., Very suitable for hot foil stamping, Suitability of foils must be checked		

Application Method

• Blanket, Flexo or Chambered Anilox Coaters, 10-14 bcm

Substrate Recommendation

- Coated Board
- Coated Paper



Technical Data Sheet

ULTRASHEEN® UV-9671BF

UV curable gloss benzophenone-free foil stampable coating

ACTEGA North America, Inc.

1450 Taylors Lane, Cinnaminson, NJ 08077 US +1 800-255-0021 info.ACTEGA.northamerica@altana.com www.actega.com

Properties

Gloss 00000000 Flexibility 00000000 **000000000** Scuff Resistance Hot Foil Stamping 000000000 Slip Surface Smoothness ••00000000 Reactivity 00000000 Two Sided Coating **0**00000000 Counter Glueing

Product Characteristics				
Viscosity	• ~295 mPas +/- 20 (Centipoise at 25°C)			
Curing	• 125 fpm @ 300WPI			
Hot Foil Stamping	Z	Glueability	Z	
Slip Angle	Greater than 30 degrees	Anti Penetration		

Storage Instructions

- Shelf-life 6 months
- Applies to closed original containers at 5°C up to 30°C.

Cleaning Instructions

• Please clean maschines and tools with commercial cleaning agents.

Additional Information

MEK Resistance: 30 - 40 Double Rubs * Estimated chemical resistance on press



Technical Data Sheet ULTRASHEEN® UV-9671BF

UV curable gloss benzophenone-free foil stampable coating

ACTEGA North America, Inc. 1450 Taylors Lane, Cinnaminson, NJ 08077 US +1 800-255-0021 info.ACTEGA.northamerica@altana.com www.actega.com

Disclaimer

The characteristics contained herein constitute binding product specifications which we warrant provided the conditions and testing methods mentioned therein are used. Any other subjective or objective requirements concerning the products are excluded. Any information herein about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. No warranties of merchantability or fitness for a particular purpose are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.